

SUORITUSTASOILMOITUS

DoP Nro: MKT-2.1-700_fi

- ✧ **Tuotetyypin yksilöllinen tunniste:** Ruiskutusjärjestelmä VME plus
- ✧ **Aiottu käyttötarkoitus (aiotut käyttötarkoitukset):** Injektionestojärjestelmä ankkurointi betoniin, katso liite / Annex B
- ✧ **Valmistaja:** MKT Metall-Kunststoff-Technik GmbH & Co.KG
Auf dem Immel 2
67685 Weilerbach
- ✧ **Rakennustuotteen suoritustason pysyvyyden arviointi- ja varmennusjärjestelmä(t):** 1
- ✧ **Eurooppalainen arviointiasiakirja:** EAD 330499-01-0601
Eurooppalainen tekninen arviointi: ETA-19/0483, 30.08.2019
Teknisestä arvioinnista vastaava laitos: DIBt, Berlin
Ilmoitettu laitos/ilmoitetut laitokset: NB 2873 – Technische Universität Darmstadt

✧ **Ilmoitettu suoritustaso/ilmoitetut suoritustasot:**

Olellaiset ominaisuudet	Suoritustaso
Mekaaninen lujuus ja vakaus (BWR 1)	
Ominaisresistanssit vetolujuudessa (staattiset ja lähes staattiset vaikutukset)	Liite / Annex C1, C3, C4, C7, C9
Ominaisresistanssit poikittaisessa rasituksessa (staattiset ja lähes staattiset vaikutukset)	Liite / Annex C2, C5, C8, C10
Vuorossa (staattiset ja lähes staattiset vaikutukset)	Liite / Annex C12 – C14
Ominaisvastus ja siirtymät seismiselle suorituskykyluokalle C1 + C2	Liite / Annex C6, C11, C12
Kierrätettävyys	Liite / Annex B1
Hygienia, terveys ja ympäristö (BWR 3)	
Vaarallisten aineiden pitoisuus, päästöt ja / tai päästöt	Suorituskykyä ei arvioitu

Edellä yksilöidyn tuotteen suoritustaso on ilmoitettujen suoritustasojen joukon mukainen. Tämä suoritustasoilmoitus on asetuksen (EU) N:o 305/2011 mukaisesti annettu edellä ilmoitetun valmistajan yksinomaisella vastuulla.

Valmistajan puolesta allekirjoittanut:



Stefan Weustenhagen
(Toimitusjohtaja)
Weilerbach, 01.01.2021

p.p. 
Dipl.-Ing. Detlef Bigalke
(Tuotekehityksen johtaja)



Tämän suoritusilmoituksen alkuperäinen teksti on kirjoitettu saksaksi. Jos käännökset poikkeavat toisistaan, saksankielinen versio on pätevä.

Specification of intended use

Injection System VME plus	Threaded rod	Internally threaded anchor rod	Rebar
Static or quasi-static action	M8 - M30 zinc plated, A2, A4, HCR	VMU-IG M6 - VMU-IG M20 zinc plated, A4, HCR	Ø8 - Ø32
Seismic action, category C1	M8 - M30 zinc plated ¹⁾ , A4, HCR	-	Ø8 - Ø32
Seismic action, category C2	M12 – M24 zinc plated ¹⁾ (property class 8.8), A4, HCR property class ≥ 70)	-	-
Base materials	compacted, reinforced or unreinforced normal weight concrete (without fibers) acc. to EN 206:2013		
	strength classes acc. to EN 206:2013: C20/25 to C50/60		
	cracked or uncracked concrete		
Temperature Range I	-40 °C to +40 °C	max. long term temperature +24 °C and max. short term temperature +40 °C	
Temperature Range II	-40 °C to +72 °C	max. long term temperature +50 °C and max. short term temperature +72 °C	

¹⁾ except hot-dip galvanized

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (all materials).
- For all other conditions according to EN 1993-1-4:2006+A1:2015 corresponding to corrosion resistance classes:
 - Stainless steel A2 according to Annex A 4, Table A1: CRC II
 - Stainless steel A4 according to Annex A 4, Table A1: CRC III
 - High corrosion resistant steel HCR according to Annex A 4, Table A1: CRC V

Design:

- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.)
- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work
- Anchorages are designed in accordance with EN 1992-4:2018 or Technical Report TR 055, February 2018

Installation:

- Dry or wet concrete or waterfilled boreholes (not seawater)
- Hole drilling by hammer drill, compressed air drill or vacuum drill mode
- Overhead installation allowed
- Anchor installation carried out by appropriately qualified personnel and under the responsibility of the person responsible for technical matters of the site
- Internally threaded anchor rod: Screws and threaded rods (incl. nut and washer) must at least correspond to the material and strength class of the internally threaded anchor rod used

Injection System VME plus

Intended use
Specifications

Annex B1

Table B1: Installation parameters for threaded rods

Threaded rod		M8	M10	M12	M16	M20	M24	M27	M30
Diameter of threaded rod	$d=d_{nom}$ [mm]	8	10	12	16	20	24	27	30
Nominal drill hole diameter	d_0 [mm]	10	12	14	18	22	28	30	35
Effective anchorage depth	$h_{ef,min}$ [mm]	60	60	70	80	90	96	108	120
	$h_{ef,max}$ [mm]	160	200	240	320	400	480	540	600
Diameter of clearance hole in the fixture	Pre-setting installation $d_f \leq$ [mm]	9	12	14	18	22	26	30	33
	Through setting installation $d_f \leq$ [mm]	12	14	16	20	24	30	33	40
Installation torque	$T_{inst} \leq$ [Nm]	10	20	40 (35) ¹⁾	60	100	170	250	300
Minimum thickness of member	h_{min} [mm]	$h_{ef} + 30mm \geq 100mm$			$h_{ef} + 2d_0$				
Minimum spacing	s_{min} [mm]	40	50	60	75	95	115	125	140
Minimum edge distance	c_{min} [mm]	35	40	45	50	60	65	75	80

¹⁾ Installation torque for property class 4.6

Table B2: Installation parameters for internally threaded anchor rods

Internally threaded anchor rod		IG-M 6	IG-M 8	IG-M 10	IG-M 12	IG-M 16	IG-M 20
Inner diameter of threaded rod	d_2 [mm]	6	8	10	12	16	20
Outer diameter of threaded rod ¹⁾	$d=d_{nom}$ [mm]	10	12	16	20	24	30
Nominal drill hole diameter	d_0 [mm]	12	14	18	22	28	35
Effective anchorage depth	$h_{ef,min}$ [mm]	60	70	80	90	96	120
	$h_{ef,max}$ [mm]	200	240	320	400	480	600
Diameter of clearance hole in the fixture	$d_f \leq$ [mm]	7	9	12	14	18	22
Installation torque	$T_{inst} \leq$ [Nm]	10	10	20	40	60	100
Minimum screw-in depth	l_{IG} [mm]	8	8	10	12	16	20
Minimum thickness of member	h_{min} [mm]	$h_{ef} + 30mm \geq 100mm$		$h_{ef} + 2d_0$			
Minimum spacing	s_{min} [mm]	50	60	75	95	115	140
Minimum edge distance	c_{min} [mm]	40	45	50	60	65	80

¹⁾ With metric thread acc. to EN 1993-1-8:2005+AC:2009

Table B3: Installation parameters for rebar

Rebar		Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 24	Ø 25	Ø 28	Ø 32
Diameter of rebar	$d=d_{nom}$ [mm]	8	10	12	14	16	20	24	25	28	32
Nominal drill hole diameter ¹⁾	d_0 [mm]	10 12	12 14	14 16	18	20	25	32	32	35	40
Effective anchorage depth	$h_{ef,min}$ [mm]	60	60	70	75	80	90	96	100	112	128
	$h_{ef,max}$ [mm]	160	200	240	280	320	400	480	500	560	640
Minimum thickness of member	h_{min} [mm]	$h_{ef} + 30 mm \geq 100 mm$			$h_{ef} + 2d_0$						
Minimum spacing	s_{min} [mm]	40	50	60	70	75	95	120	120	130	150
Minimum edge distance	c_{min} [mm]	35	40	45	50	50	60	70	70	75	85

¹⁾ For Ø8, Ø10 and Ø12 both nominal drill hole diameter can be used

Injection System VME plus

Intended use
Installation parameters

Annex B2

Table B4: Parameter for cleaning and setting tools








Threaded rod 	Internally threaded anchor rod 	Rebar 	Drill bit Ø 	Brush Ø 	min. Brush Ø
[-]	[-]	Ø [mm]	d ₀ [mm]	d _b [mm]	d _{b,min} [mm]
M8		8	10	11,5	10,5
M10	VMU-IG M6	8 / 10	12	13,5	12,5
M12	VMU-IG M8	10 / 12	14	15,5	14,5
		12	16	17,5	16,5
M16	VMU-IG M10	14	18	20,0	18,5
		16	20	22,0	20,5
M20	VMU-IG M12		22	24,0	22,5
		20	25	27,0	25,5
M24	VMU-IG M16		28	30,0	28,5
M27			30	31,8	30,5
		24 / 25	32	34,0	32,5
M30	VMU-IG M20	28	35	37,0	35,5
		32	40	43,5	40,5

Table B5: Retaining washer

Drill bit Ø 		Installation direction and use		
d ₀ [mm]	[-]	↓	→	↑
10	No retaining washer required			
12				
14				
16				
18	VM-IA 18	h _{ef} > 250mm	h _{ef} > 250mm	all
20	VM-IA 20			
22	VM-IA 22			
25	VM-IA 25			
28	VM-IA 28			
30	VM-IA 30			
32	VM-IA 32			
35	VM-IA 35			
40	VM-IA 40			



Vacuum drill bit

Vacuum drill bit (MKT Hollow drill bit SB, Würth Hammer drill bit with suction or Heller Duster Expert hollow drill bit system) and a vacuum cleaner with minimum negative pressure of 253 hPa and flow rate of minimum 42 l/s



Recommended compressed air tool (min 6 bar)

Drill bit diameter (d₀): all diameters

Injection System VME plus

Intended use
Cleaning and setting tools

Annex B3

Table B6: Working time and curing time









Concrete temperature	Working time	Minimum curing time	
		dry concrete	wet concrete
+5°C to +9°C	80 min	48 h	96 h
+10°C to +14°C	60 min	28 h	56 h
+15°C to +19°C	40 min	18 h	36 h
+20°C to +24°C	30 min	12 h	24 h
+25°C to +34°C	12 min	9 h	18 h
+35°C to +39°C	8 min	6 h	12 h
+40°C	8 min	4 h	8 h
Cartridge temperature	+5°C to +40°C		

Injection System VME plus

Intended use
Working and curing time

Annex B4

Installation Instructions

Drilling of the hole		
1a		<p>Hammer drilling or compressed air drilling Drill with hammer drill or compressed air drill a hole into the base material with prescribed nominal drill hole diameter (Table B1, B2 or B3) and selected borehole depth. Continue with <u>step 2</u>. In case of aborted drill hole, the drill hole shall be filled with mortar.</p>
1b		<p>Vacuum drilling: see Annex B3 Drill borehole with prescribed nominal drill hole diameter (Table B1, B2 or B3) and selected borehole depth. This drilling method removes dust and cleans the borehole during drilling. Continue with <u>step 3</u>. In case of aborted drill hole, the drill hole shall be filled with mortar.</p>
Attention! Standing water in the bore hole must be removed before cleaning!		
Cleaning (Not applicable when using vacuum drilling – see step 1b and Annex B3)		
2a		<p>Starting from the bottom or back of the bore hole, blow out the hole with compressed air (min. 6 bar) a minimum of two times until return air stream is free of noticeable dust. If the borehole ground is not reached, an extension must be used.</p>
2b		<p>Check brush diameter (Table B4). Brush the hole with an appropriate sized wire brush $\geq d_{b,min}$ (Table B4) a minimum of two times. If the borehole ground is not reached with the brush, an appropriate brush extension must be used.</p>
2c		<p>Starting from the bottom or back of the bore hole, blow out the hole with compressed air (min. 6 bar) again a minimum of two times until return air stream is free of noticeable dust. If the borehole ground is not reached, an extension must be used.</p>
<p>After cleaning, the borehole has to be protected against re-contamination in an appropriate way, until dispensing the mortar in the borehole. If necessary, the cleaning has to be repeated directly before dispensing the mortar. In-flowing water must not contaminate the borehole again.</p>		
Preparation Injection		
3		<p>Attach the supplied static-mixing nozzle to the cartridge and load the cartridge into the correct dispensing tool. For every working interruption longer than the recommended working time (Table B6) as well as for new cartridges, a new static-mixer shall be used.</p>
4		<p>Prior to inserting the rod into the filled borehole, the position of the embedment depth shall be marked on the threaded rod or rebar.</p>
5		<p>Prior to dispensing into the drill hole, squeeze out separately a minimum of three full strokes and discard non-uniformly mixed adhesive components until the mortar shows a consistent grey or red colour.</p>

Injection System VME plus

Intended Use
 Installation instructions

Annex B5

Installation instructions (continue)

Injection		
6a		Starting from the bottom or back of the cleaned drill hole fill the hole up to approximately two-thirds with adhesive. Slowly withdraw the static mixing nozzle as the hole fills to avoid air pockets. If the bore hole ground is not reached, an appropriate extension nozzle shall be used. Observe temperature dependent working times given in Table B6.
6b		Retaining washer and mixer nozzle extensions shall be used according to Table B5 for the following applications: <ul style="list-style-type: none"> • Horizontal installation (horizontal direction) and ground installation (vertical downwards direction): Drill bit-$\varnothing d_0 \geq 18$ mm and anchorage depth $h_{ef} > 250$mm • Overhead installation: Drill bit-$\varnothing d_0 \geq 18$ mm
Inserting the anchor		
7		Push the threaded rod or reinforcing bar into the hole while turning slightly to ensure proper distribution of the adhesive until the embedment depth is reached. The anchor shall be free of dirt, grease, oil or other foreign material.
8		Make sure that excess mortar is visible at the top of the hole and in case of through-setting installation also in the fixture. If these requirements are not maintained, repeat application before end of working time! For overhead installation, the anchor should be fixed (e.g. by wedges).
9		Allow the adhesive to cure to the specified time prior to applying any load or torque. Do not move or load the anchor until it is fully cured (attend Table B6).
10		Remove excess mortar.
11		The fixture can be mounted after curing time. Apply installation torque T_{inst} according to Table B1 or B2.
12		In case of pre-setting installation the annular gap between anchor rod and fixture can optionally be filled with mortar. Therefore, replace regular washer by washer with bore and plug on reducing adapter on static mixer. Annular gap is completely filled, when excess mortar seeps out.

Injection System VME plus

Intended Use
Installation instructions (continuation)

Annex B6

Table C1: Characteristic steel resistance for threaded rods under tension load

Threaded rod				M8	M10	M12	M16	M20	M24	M27	M30
Steel failure											
Cross sectional area A_s [mm ²]				36,6	58,0	84,3	157	245	353	459	561
Characteristic resistance under tension load ¹⁾											
Steel, zinc plated	Property class 4.6 and 4.8	$N_{Rk,s}$	[kN]	15 (13)	23 (21)	34	63	98	141	184	224
	Property class 5.6 and 5.8	$N_{Rk,s}$	[kN]	18 (17)	29 (27)	42	78	122	176	230	280
	Property class 8.8	$N_{Rk,s}$	[kN]	29 (27)	46 (43)	67	125	196	282	368	449
Stainless steel	A2, A4 and HCR Property class 50	$N_{Rk,s}$	[kN]	18	29	42	79	123	177	230	281
	A2, A4 and HCR Property class 70	$N_{Rk,s}$	[kN]	26	41	59	110	171	247	-	-
	A4 and HCR Property class 80	$N_{Rk,s}$	[kN]	29	46	67	126	196	282	-	-
Partial factors ²⁾											
Steel, zinc plated	Property class 4.6	$\gamma_{Ms,N}$	[-]	2,0							
	Property class 4.8	$\gamma_{Ms,N}$	[-]	1,5							
	Property class 5.6	$\gamma_{Ms,N}$	[-]	2,0							
	Property class 5.8	$\gamma_{Ms,N}$	[-]	1,5							
	Property class 8.8	$\gamma_{Ms,N}$	[-]	1,5							
Stainless steel	A2, A4 and HCR Property class 50	$\gamma_{Ms,N}$	[-]	2,86							
	A2, A4 and HCR Property class 70	$\gamma_{Ms,N}$	[-]	1,87						-	-
	A4 and HCR Property class 80	$\gamma_{Ms,N}$	[-]	1,6						-	-

¹⁾ The characteristic resistances apply for all anchor rods with the cross sectional area A_s specified here: VMU-A, V-A, VM-A
For commercial standard threaded rods with a smaller cross sectional area (e.g. hot-dip galvanized threaded rods M8, M10 according to EN ISO 10664:2004 + AC:2009), the values in brackets are valid.

²⁾ in absence of national regulation

Injection System VME plus

Performance

Characteristic **steel resistance** for **threaded rods** under **tension load**

Annex C1

Table C2: Characteristic steel resistance for threaded rods under shear load

Threaded rod				M8	M10	M12	M16	M20	M24	M27	M30
Steel failure											
Cross sectional area A_s [mm ²]				36,6	58,0	84,3	157	245	353	459	561
Characteristic resistance under shear load ¹⁾											
Steel failure <u>without</u> lever arm											
Steel, zinc plated	Property class 4.6 and 4.8	$V_{Rk,s}^0$ [kN]	9 (8)	14 (13)	20	38	59	85	110	135	
	Property class 5.6 and 5.8	$V_{Rk,s}^0$ [kN]	11 (10)	17 (16)	25	47	74	106	138	168	
	Property class 8.8	$V_{Rk,s}^0$ [kN]	15 (13)	23 (21)	34	63	98	141	184	224	
Stainless steel	A2, A4 and HCR, property class 50	$V_{Rk,s}^0$ [kN]	9	15	21	39	61	88	115	140	
	A2, A4 and HCR, property class 70	$V_{Rk,s}^0$ [kN]	13	20	30	55	86	124	-	-	
	A4 and HCR, property class 80	$V_{Rk,s}^0$ [kN]	15	23	34	63	98	141	-	-	
Steel failure <u>with</u> lever arm											
Steel, zinc plated	Property class 4.6 and 4.8	$M_{Rk,s}^0$ [Nm]	15 (13)	30 (27)	52	133	260	449	666	900	
	Property class 5.6 and 5.8	$M_{Rk,s}^0$ [Nm]	19 (16)	37 (33)	65	166	324	560	833	1123	
	Property class 8.8	$M_{Rk,s}^0$ [Nm]	30 (26)	60 (53)	105	266	519	896	1333	1797	
Stainless steel	A2, A4 and HCR, property class 50	$M_{Rk,s}^0$ [Nm]	19	37	66	167	325	561	832	1125	
	A2, A4 and HCR, property class 70	$M_{Rk,s}^0$ [Nm]	26	52	92	232	454	784	-	-	
	A4 and HCR, property class 80	$M_{Rk,s}^0$ [Nm]	30	59	105	266	519	896	-	-	
Partial factor ²⁾											
Steel, zinc plated	Property class 4.6	$\gamma_{Ms,V}$ [-]	1,67								
	Property class 4.8	$\gamma_{Ms,V}$ [-]	1,25								
	Property class 5.6	$\gamma_{Ms,V}$ [-]	1,67								
	Property class 5.8	$\gamma_{Ms,V}$ [-]	1,25								
	Property class 8.8	$\gamma_{Ms,V}$ [-]	1,25								
Stainless steel	A2, A4 and HCR, property class 50	$\gamma_{Ms,V}$ [-]	2,38								
	A2, A4 and HCR, property class 70	$\gamma_{Ms,V}$ [-]	1,56						-	-	
	A4 and HCR, property class 80	$\gamma_{Ms,V}$ [-]	1,33						-	-	

¹⁾ The characteristic resistances apply for all anchor rods with the cross sectional area A_s specified here: VMU-A, V-A, VM-A
For commercial standard threaded rods with a smaller cross sectional area (e.g. hot-dip galvanized threaded rods M8, M10 according to EN ISO 10684:2004 + AC:2009), the values in brackets are valid.

²⁾ in absence of national regulation

Injection System VME plus

Performance
Characteristic **steel resistance** for **threaded rods** under **shear load**

Annex C2

Table C3: Characteristic values for **concrete cone** and **splitting failure**

Threaded rods / Internally threaded anchor rods / Rebar				all sizes
Concrete cone failure				
Factor k_1	uncracked concrete	$k_{ucr,N}$	[-]	11,0
	cracked concrete	$k_{cr,N}$	[-]	7,7
Edge distance		$c_{cr,N}$	[mm]	$1,5 \cdot h_{ef}$
Spacing		$s_{cr,N}$	[mm]	$2 \cdot c_{cr,N}$
Splitting failure				
Edge distance	$h/h_{ef} \geq 2,0$	$c_{cr,sp}$	[mm]	$1,0 \cdot h_{ef}$
	$2,0 > h/h_{ef} > 1,3$			$2 \cdot h_{ef} (2,5 - h / h_{ef})$
	$h/h_{ef} \leq 1,3$			$2,4 \cdot h_{ef}$
Spacing		$s_{cr,sp}$	[mm]	$2 \cdot c_{cr,sp}$

Injection System VME plus

Performance
 Characteristic values for **concrete cone** and **splitting failure**

Annex C3

Table C4: Characteristic values of **tension load** for **threaded rods** under **static** and **quasi-static** action

Threaded rod				M8	M10	M12	M16	M20	M24	M27	M30
Steel failure											
Characteristic resistance		$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}$ (or see Table C1)							
Partial factor		$\gamma_{Ms,N}$	[-]	see Table C1							
Combined pull-out and concrete failure											
Characteristic bond resistance in <u>uncracked</u> concrete C20/25											
Temperature range I: 40°C / 24°C	Hammer- or compressed air drilling	$\tau_{Rk,ucr}$	[N/mm ²]	20	20	19	19	18	17	16	16
Temperature range II: 72°C / 50°C		$\tau_{Rk,ucr}$	[N/mm ²]	15	15	15	14	13	13	12	12
Temperature range I: 40°C / 24°C	Vacuum drilling	$\tau_{Rk,ucr}$	[N/mm ²]	17 (16) ¹⁾	16	16	16 (15) ¹⁾	15	14	14	13
Temperature range II: 72°C / 50°C		$\tau_{Rk,ucr}$	[N/mm ²]	14	14	14	13	13	12	12	11
Characteristic bond resistance in <u>cracked</u> concrete C20/25											
Temperature range I: 40°C / 24°C	all drilling methods	$\tau_{Rk,cr}$	[N/mm ²]	7,0	7,0	8,5	8,5	8,5	8,5	8,5	8,5
Temperature range II: 72°C / 50°C		$\tau_{Rk,cr}$	[N/mm ²]	6,0	6,0	7,0	7,0	7,0	7,0	7,0	7,0
Reductionfactor ψ_{sus}^0 in concrete C20/25											
Temperature range I: 40°C / 24°C	all drilling methods	ψ_{sus}^0	[-]	0,75							
Temperature range II: 72°C / 50°C		ψ_{sus}^0	[-]	0,68							
Increasing factors for concrete	C25/30	ψ_c	[-]	1,02							
	C30/37		[-]	1,04							
	C35/45		[-]	1,07							
	C40/50		[-]	1,08							
	C45/55		[-]	1,09							
	C50/60		[-]	1,10							
Concrete cone failure											
Relevant parameter				see Table C3							
Splitting failure											
Relevant parameter				see Table C3							
Installation factor											
Dry or wet concrete		γ_{inst}	[-]	1,0							
Waterfilled bore hole		γ_{inst}	[-]	1,2							

¹⁾ Value in brackets: characteristic bond resistance for waterfilled bore holes

Injection System VME plus

Performance
Characteristic values of **tension loads** for **threaded rods**

Annex C4

Table C5: Characteristic values of shear loads for threaded rods under static and quasi-static action

Threaded rod			M8	M10	M12	M16	M20	M24	M27	M30	
Steel failure <u>without</u> lever arm											
Characteristic shear resistance Steel, property class 4.6, 4.8, 5.6 and 5.8	$V_{Rk,s}^0$	[kN]	0,6 · A _s · f _{uk} or see Table C2								
Characteristic shear resistance Steel, property class 8.8 Stainless steel A2, A4 and HCR (all property classes)	$V_{Rk,s}^0$	[kN]	0,5 · A _s · f _{uk} or see Table C2								
Ductility factor	k ₇	[-]	1,0								
Partial factor	γ _{Ms,V}	[-]	see Table C2								
Steel failure <u>with</u> lever arm											
Characteristic bending resistance	$M_{Rk,s}^0$	[Nm]	1,2 · W _{el} · f _{uk} or see Table C2								
Elastic section modulus	W _{el}	[mm ³]	31	62	109	277	541	935	1387	1874	
Partial factor	γ _{Ms,V}	[-]	see Table C2								
Concrete pry-out failure											
Pry-out factor	k ₈	[-]	2,0								
Concrete edge failure											
Effective length of anchor	l _f	[mm]	min (h _{ef} ; 12 d _{nom})							min (h _{ef} ; 300mm)	
Outside diameter of anchor	d _{nom}	[mm]	8	10	12	16	20	24	27	30	
Installation factor	γ _{inst}	[-]	1,0								

Injection System VME plus

Performance
Characteristic values of **shear loads** for **threaded rods**

Annex C5

Table C6: Characteristic values of **tension load** for **threaded rods** under **seismic action** (performance category **C1 + C2**)

Threaded rod				M8	M10	M12	M16	M20	M24	M27	M30
Tension loads											
Steel failure											
Characteristic resistance C1	$N_{Rk,s,eq,C1}$	[kN]	$1,0 \cdot N_{Rk,s}$								
Characteristic resistance C2 steel, zinc plated, property class 8.8 stainless steel A4 and HCR, property class ≥ 70	$N_{Rk,s,eq,C2}$	[kN]	NPA	$1,0 \cdot N_{Rk,s}$						NPA	
Partial factor	$\gamma_{Ms,N}$	[-]	see Table C1								
Combined pull-out and concrete failure											
Characteristic bond resistance in concrete C20/25											
Temperature range I: 40°C / 24°C	all drilling methods	$\tau_{Rk,eq,C1}$ [N/mm ²]	7,0	7,0	8,5	8,5	8,5	8,5	8,5	8,5	8,5
		$\tau_{Rk,eq,C2}$ [N/mm ²]	NPA		5,8	4,8	5,0	5,1	NPA		
Temperature range II: 72°C / 50°C		$\tau_{Rk,eq,C1}$ [N/mm ²]	6,0	6,0	7,0	7,0	7,0	7,0	7,0	7,0	7,0
$\tau_{Rk,eq,C2}$ [N/mm ²]		NPA		5,0	4,1	4,3	4,4	NPA			
Installation factor											
Dry or wet concrete	γ_{inst}	[-]	1,0								
Waterfilled bore hole	γ_{inst}	[-]	1,2								

Table C7: Characteristic values of **shear loads** for **threaded rods** under **seismic action** (performance category **C1 + C2**)

Shear loads											
Steel failure <u>without</u> lever arm											
Characteristic resistance C1	$V_{Rk,s,eq,C1}$	[kN]	$0,7 \cdot V_{Rk,s}^0$								
Characteristic resistance C2 steel, zinc plated, property class 8.8 stainless steel A4 and HCR, property class ≥ 70	$V_{Rk,s,eq,C2}$	[kN]	No Performance Assessed (NPA)	$0,7 \cdot V_{Rk,s}^0$						No Performance Assessed (NPA)	
Steel failure <u>with</u> lever arm											
Characteristic bending resistance	$M_{Rk,s,eq,C1}^0$	[Nm]	No Performance Assessed (NPA)								
	$M_{Rk,s,eq,C2}^0$	[Nm]	No Performance Assessed (NPA)								
Installation factor	γ_{inst}	[-]	1,0								
Factor for annular gap	α_{gap}	[-]	$1,0 (0,5)^{1)}$								

¹⁾ Value in bracket is valid for fastenings with annular gap between threaded rod and fixture

Injection System VME plus

Performance
Characteristic values for **threaded rods** under **seismic action**

Annex C6

Table C8: Characteristic values of **tension loads** for **internally threaded anchor rod** under **static** and **quasi-static** action

Internally threaded anchor rod				VMU-IG M 6	VMU-IG M 8	VMU-IG M 10	VMU-IG M 12	VMU-IG M 16	VMU-IG M 20
Steel failure ¹⁾									
Characteristic resistance, steel, zinc plated, property class	5.8	$N_{Rk,s}$	[kN]	10	17	29	42	76	123
	8.8	$N_{Rk,s}$	[kN]	16	27	46	67	121	196
Partial factor 5.8 and 8.8		$\gamma_{Ms,N}$	[-]	1,5					
Characteristic resistance, Stainless steel A4 / HCR, property class 70		$N_{Rk,s}$	[kN]	14	26	41	59	110	124 ²⁾
	Partial factor		$\gamma_{Ms,N}$	[-]	1,87				
Combined pull-out and concrete failure									
Characteristic bond resistance in <u>uncracked</u> concrete C20/25									
Temperature range I: 40°C / 24°C	Hammer- or compressed air drilling	$\tau_{Rk,ucr}$	[N/mm ²]	20	19	19	18	17	16
Temperature range II: 72°C / 50°C		$\tau_{Rk,ucr}$	[N/mm ²]	15	15	14	13	13	12
Temperature range I: 40°C / 24°C	Vacuum drilling	$\tau_{Rk,ucr}$	[N/mm ²]	16	16	16 (15) ³⁾	15	14	13
Temperature range II: 72°C / 50°C		$\tau_{Rk,ucr}$	[N/mm ²]	14	14	13	13	12	11
Characteristic bond resistance in <u>cracked</u> concrete C20/25									
Temperature range I: 40°C / 24°C	all drilling methods	$\tau_{Rk,cr}$	[N/mm ²]	7,0	8,5	8,5	8,5	8,5	8,5
Temperature range II: 72°C / 50°C		$\tau_{Rk,cr}$	[N/mm ²]	6,0	7,0	7,0	7,0	7,0	7,0
Reductionfactor ψ_{sus}^0									
Temperature range I: 40°C / 24°C	all drilling methods	ψ_{sus}^0	[-]	0,75					
Temperature range II: 72°C / 50°C		ψ_{sus}^0	[-]	0,68					
Increasing factor for concrete		ψ_c	C25/30	1,02					
			C30/37	1,04					
			C35/45	1,07					
			C40/50	1,08					
			C45/55	1,09					
			C50/60	1,10					
Concrete cone failure									
Relevant parameter				see Table C3					
Splitting failure									
Relevant parameter				see Table C3					
Installation factor									
Dry or wet concrete		γ_{inst}	[-]	1,0					
Waterfilled bore hole		γ_{inst}	[-]	1,2					

¹⁾ Fastening screws or threaded rods (incl. nut and washer) must comply with the appropriate material and property class of the internally threaded anchor rod. The characteristic tension resistance for steel failure of the given strength class are valid for the internally threaded anchor rod and the fastening element.

²⁾ For VMU-IG M20: property class 50

³⁾ Value in bracket is valid for waterfilled bore hole

Injection System VME plus

Performance

Characteristic values of **tension loads** for **internally threaded anchor rod**

Annex C7

Table C9: Characteristic values of shear loads for internally threaded anchor rod under static and quasi-static action

Internally threaded anchor rod				VMU-IG M 6	VMU-IG M 8	VMU-IG M 10	VMU-IG M 12	VMU-IG M 16	VMU-IG M 20
Steel failure <u>without</u> lever arm ¹⁾									
Steel, zinc plated	Characteristic resistance, property class	5.8	$V_{RK,s}^0$ [kN]	5	9	15	21	38	61
		8.8	$V_{RK,s}^0$ [kN]	8	14	23	34	60	98
	Partial factor 5.8 and 8.8		$\gamma_{Ms,v}$	[-]	1,25				
Stainless steel	Characteristic resistance, A4 / HCR, property class 70		$V_{RK,s}^0$ [kN]	7	13	20	30	55	62 ²⁾
	Partial factor		$\gamma_{Ms,v}$	[-]	1,56				
Ductility factor			k_7	[-]	1,0				
Steel failure <u>with</u> lever arm ¹⁾									
Steel, zinc plated	Characteristic bending resistance, property class	5.8	$M_{RK,s}^0$ [Nm]	8	19	37	66	167	325
		8.8	$M_{RK,s}^0$ [Nm]	12	30	60	105	267	519
	Partial factor 5.8 and 8.8		$\gamma_{Ms,v}$	[-]	1,25				
Stainless steel	Characteristic bending resistance A4 / HCR, property class 70		$M_{RK,s}^0$ [Nm]	11	26	53	92	234	643 ²⁾
	Partial factor		$\gamma_{Ms,v}$	[-]	1,56				
Concrete pry-out failure									
Pry-out factor			k_8	[-]	2,0				
Concrete edge failure									
Effective length of anchor			l_f [mm]	min ($h_{ef}; 12 d_{nom}$)					min ($h_{ef}; 300mm$)
Outside diameter of anchor			d_{nom} [mm]	10	12	16	20	24	30
Installation factor			γ_{inst}	[-]	1,0				

¹⁾ Fastening screws or threaded rods (incl. nut and washer) must comply with the appropriate material and property class of the internally threaded anchor rod (exception: VMU-IG M20). The characteristic shear resistance for steel failure of the given strength class are valid for the internally threaded anchor rod and the fastening element.

²⁾ For VMU-IG M20: Internally threaded rod: property class 50;
Fastening screws or threaded rods (incl. nut and washer): property class 70

Injection System VME plus

Performance

Characteristic values of **shear loads** for **internally threaded anchor rod**

Annex C8

Table C10: Characteristic values of tension loads for rebar under static and quasi-static action

Reinforcing bar			Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 24	Ø 25	Ø 28	Ø 32	
Steel failure													
Characteristic tension resistance	$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}^{1)}$										
Cross sectional area	A_s	[mm ²]	50	79	113	154	201	314	452	491	616	804	
Partial factor	$\gamma_{Ms,N}$	[-]	1,4 ²⁾										
Combined pull-out and concrete failure													
Characteristic bond resistance in <u>uncracked</u> concrete C20/25													
Temperature range I: 40°C / 24°C	Hammer- or compressed air drilling	$\tau_{Rk,ucr}$	[N/mm ²]	16	16	16	16	16	16	15	15	15	15
Temperature range II: 72°C / 50°C		$\tau_{Rk,ucr}$	[N/mm ²]	12	12	12	12	12	12	12	12	11	11
Temperature range I: 40°C / 24°C	Vacuum drilling	$\tau_{Rk,ucr}$	[N/mm ²]	14 (13) ³⁾	14 (13) ³⁾	13	13	13	13	13	13	13	13
Temperature range II: 72°C / 50°C		$\tau_{Rk,ucr}$	[N/mm ²]	12 (11) ³⁾	12 (11) ³⁾	12 (11) ³⁾	11	11	11	11	11	11	11
Characteristic bond resistance in <u>cracked</u> concrete C20/25													
Temperature range I: 40°C / 24°C	all drilling methods	$\tau_{Rk,cr}$	[N/mm ²]	7,0	7,0	8,5	8,5	8,5	8,5	8,5	8,5	8,5	8,5
Temperature range II: 72°C / 50°C		$\tau_{Rk,cr}$	[N/mm ²]	6,0	6,0	7,0	7,0	7,0	7,0	7,0	7,0	7,0	7,0
Reductionfactor ψ_{sus}^0													
Temperature range I: 40°C / 24°C	all drilling methods	ψ_{sus}^0	[-]	0,75									
Temperature range II: 72°C / 50°C		ψ_{sus}^0	[-]	0,68									
Increasing factor for concrete		ψ_c	C25/30	1,02									
			C30/37	1,04									
			C35/45	1,07									
			C40/50	1,08									
			C45/55	1,09									
			C50/60	1,10									
Concrete cone failure													
Relevant parameter			see Table C3										
Splitting failure													
Relevant parameter			see Table C3										
Installation factor													
Dry or wet concrete		γ_{inst}	[-]	1,0									
Waterfilled bore hole		γ_{inst}	[-]	1,2									

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ in absence of national regulation

³⁾ Value in brackets: characteristic bond resistance for waterfilled bore holes

Injection System VME plus

Annex C9

Performance

Characteristic values of **tension loads** for rebar

Table C11: Characteristic values of shear loads for rebar under static and quasi-static action

Reinforcing bar		Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 24	Ø 25	Ø 28	Ø 32	
Steel failure <u>without</u> lever arm												
Characteristic shear resistance	$V_{Rk,s}^0$ [kN]	$0,50 \cdot A_s \cdot f_{uk}^{1)}$										
Cross sectional area	A_s [mm ²]	50	79	113	154	201	314	452	491	616	804	
Partial factor	$\gamma_{Ms,V}$ [-]	1,5 ²⁾										
Ductility factor	k_7 [-]	1,0										
Steel failure <u>with</u> lever arm												
Characteristic bending resistance	$M_{Rk,s}^0$ [Nm]	$1,2 \cdot W_{el} \cdot f_{uk}^{1)}$										
Elastic section modulus	W_{el} [mm ³]	50	98	170	269	402	785	896	1534	2155	3217	
Partial factor	$\gamma_{Ms,V}$ [-]	1,5 ²⁾										
Concrete pry-out failure												
Pry-out factor	k_8 [-]	2,0										
Concrete edge failure												
Effective length of rebar	l_f [mm]	min ($h_{ef}; 12 d_{nom}$)							min ($h_{ef}; 300mm$)			
Outside diameter of rebar	d_{nom} [mm]	8	10	12	14	16	20	24	25	28	32	
Installation factor	γ_{inst} [-]	1,0										

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ in absence of national regulation

Injection System VME plus

Performance
Characteristic values of **shear loads** for rebar

Annex C10

Table C12: Characteristic values of tension load for rebar under seismic action (performance category C1)

Reinforcing bar			Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 24	Ø 25	Ø 28	Ø 32
Steel failure												
Characteristic resistance	$N_{Rk,s,eq,C1}$	[kN]	$A_s \cdot f_{uk}^{1)}$									
Cross sectional area	A_s	[mm ²]	50	79	113	154	201	314	452	491	616	804
Partial factor	$\gamma_{Ms,N}$	[-]	1,4 ²⁾									
Combined pull-out and concrete failure												
Characteristic bond resistance in concrete C20/25												
Temperature range I: 40°C / 24°C	all drilling methods	$\tau_{Rk,eq,C1}$	[N/mm ²]	7,0	7,0	8,5	8,5	8,5	8,5	8,5	8,5	8,5
Temperature range II: 72°C / 50°C		$\tau_{Rk,eq,C1}$	[N/mm ²]	6,0	6,0	7,0	7,0	7,0	7,0	7,0	7,0	7,0
Installation factor												
Dry or wet concrete	γ_{inst}	[-]	1,0									
Waterfilled bore hole	γ_{inst}	[-]	1,2									

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ in absence of national regulation

Table C13: Characteristic values of shear loads for rebar under seismic action (performance category C1)

Reinforcing bar			Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 24	Ø 25	Ø 28	Ø 32
Steel failure <u>without</u> lever arm												
Characteristic resistance	$V_{Rk,s,eq,C1}$	[kN]	$0,35 \cdot A_s \cdot f_{uk}^{1)}$									
Cross sectional area	A_s	[mm ²]	50	79	113	154	201	314	452	491	616	804
Partial factor	$\gamma_{Ms,V}$	[-]	1,5 ²⁾									
Ductility factor	k_7	[-]	1,0									
Steel failure <u>with</u> lever arm												
Characteristic bending resistance	$M^0_{Rk,s,eq,C1}$	[Nm]	No Performance Assessed (NPA)									
Installation factor	γ_{inst}	[-]	1,0									

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ in absence of national regulation

Injection System VME plus

Performance

Characteristic values for rebar under seismic action

Annex C11

Table C14: Displacements under tension load¹⁾ (threaded rod)

Threaded rod			M8	M10	M12	M16	M20	M24	M27	M30
Uncracked concrete under static and quasi-static action										
Temperature range I: 40°C / 24°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,028	0,029	0,030	0,033	0,035	0,038	0,039	0,041
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,028	0,029	0,030	0,033	0,035	0,038	0,039	0,041
Temperature range II: 72°C / 50°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,038	0,039	0,040	0,044	0,047	0,051	0,052	0,055
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,047	0,049	0,051	0,055	0,059	0,064	0,067	0,070
Cracked concrete under static and quasi-static action										
Temperature range I: 40°C / 24°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,069	0,071	0,072	0,074	0,076	0,079	0,081	0,082
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,193	0,115	0,122	0,128	0,135	0,142	0,155	0,171
Temperature range II: 72°C / 50°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,092	0,095	0,096	0,099	0,102	0,106	0,109	0,110
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,259	0,154	0,163	0,172	0,181	0,189	0,207	0,229
Uncracked and cracked concrete under seismic action (C2)										
All temperature ranges	$\delta_{N,eq}$ (DLS)	[mm]	NPA	0,21	0,24	0,27	0,36	NPA		
	$\delta_{N,eq}$ (ULS)	[mm]		0,54	0,51	0,54	0,63			

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau; \quad \tau: \text{bond stress under tension load}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau;$$

Table C15: Displacements under shear load¹⁾ (threaded rod)

Threaded rod			M 8	M 10	M 12	M 16	M 20	M24	M 27	M 30
Uncracked and cracked concrete under static and quasi-static action										
All temperature ranges	δ_{V0} - factor	[mm/(kN)]	0,06	0,06	0,05	0,04	0,04	0,03	0,03	0,03
	$\delta_{V\infty}$ - factor	[mm/(kN)]	0,09	0,08	0,08	0,06	0,06	0,05	0,05	0,05
Uncracked and cracked concrete under seismic action (C2)										
All temperature ranges	$\delta_{V,eq}$ (DLS)	[mm]	NPA	3,1	3,4	3,5	4,2	NPA		
	$\delta_{V,eq}$ (ULS)	[mm]		6,0	7,6	7,3	10,9			

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0}\text{- factor} \cdot V; \quad V: \text{acting shear load}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{- factor} \cdot V;$$

Injection System VME plus

Performance
Displacements (threaded rod)

Annex C12

Table C16: Displacements under tension load¹⁾ (internally threaded anchor rod)

Internally threaded anchor rod			VMU-IG M 6	VMU-IG M 8	VMU-IG M 10	VMU-IG M 12	VMU-IG M 16	VMU-IG M 20
Uncracked concrete under static and quasi-static action								
Temperature range I: 40°C / 24°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,029	0,030	0,033	0,035	0,038	0,041
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,029	0,030	0,033	0,035	0,038	0,041
Temperature range II: 72°C / 50°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,039	0,040	0,044	0,047	0,051	0,055
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,049	0,051	0,055	0,059	0,064	0,070
Cracked concrete under static and quasi-static action								
Temperature range I: 40°C / 24°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,071	0,072	0,074	0,076	0,079	0,082
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,115	0,122	0,128	0,135	0,142	0,171
Temperature range II: 72°C / 50°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,095	0,096	0,099	0,102	0,106	0,110
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,154	0,163	0,172	0,181	0,189	0,229

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{- factor} \cdot \tau; \quad \tau: \text{bond stress under tension load}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{- factor} \cdot \tau;$$

Table C17: Displacements under shear load¹⁾ (internally threaded anchor rod)

Internally threaded anchor rod			VMU-IG M 6	VMU-IG M 8	VMU-IG M 10	VMU-IG M 12	VMU-IG M 16	VMU-IG M 20
Uncracked and cracked concrete under static and quasi-static action								
All temperature ranges	δ_{V0} - factor	[mm/(kN)]	0,07	0,06	0,06	0,05	0,04	0,04
	$\delta_{V\infty}$ - factor	[mm/(kN)]	0,10	0,09	0,08	0,08	0,06	0,06

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0}\text{- factor} \cdot V; \quad V: \text{acting shear load}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{- factor} \cdot V;$$

Injection System VME plus

Performance

Displacements (internally threaded anchor rod)

Annex C13

Table C18: Displacements under tension load¹⁾ (rebar)

Reinforcing bar			Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 24	Ø 25	Ø 28	Ø 32
Uncracked concrete under static and quasi-static action												
Temperature range I: 40°C / 24°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,028	0,029	0,030	0,031	0,033	0,035	0,038	0,038	0,040	0,043
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,015	0,015	0,016	0,017	0,017	0,019	0,020	0,020	0,021	0,023
Temperature range II: 72°C / 50°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,038	0,039	0,040	0,042	0,044	0,047	0,051	0,051	0,054	0,058
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,047	0,049	0,051	0,053	0,055	0,059	0,065	0,065	0,068	0,072
Cracked concrete under static and quasi-static action												
Temperature range I: 40°C / 24°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,069	0,071	0,072	0,073	0,074	0,076	0,079	0,079	0,081	0,084
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,115	0,122	0,128	0,135	0,142	0,155	0,171	0,171	0,181	0,194
Temperature range II: 72°C / 50°C	δ_{N0} - factor	[mm/(N/mm ²)]	0,092	0,095	0,096	0,098	0,099	0,102	0,106	0,106	0,109	0,113
	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,154	0,163	0,172	0,181	0,189	0,207	0,229	0,229	0,242	0,260

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{- factor} \cdot \tau; \quad \tau: \text{bond stress under tension load}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{- factor} \cdot \tau;$$

Table C19: Displacements under shear load¹⁾ (rebar)

Reinforcing bar			Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 24	Ø 25	Ø 28	Ø 32
Uncracked and cracked concrete under static and quasi-static action												
All temperature ranges	δ_{V0} - factor	[mm/(kN)]	0,06	0,05	0,05	0,04	0,04	0,04	0,03	0,03	0,03	0,03
	$\delta_{V\infty}$ - factor	[mm/(kN)]	0,09	0,08	0,08	0,06	0,06	0,05	0,05	0,05	0,04	0,04

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0}\text{- factor} \cdot V; \quad V: \text{acting shear load}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{- factor} \cdot V;$$

Injection System VME plus

Performance
Displacements (rebar)

Annex C14