

DICHIARAZIONE DI PRESTAZIONE

DoP N. **MKT-2.4-102**_it

- ◇ **Codice di identificazione unico del prodotto-tipo:** **Sistema di iniezione VMZ dynamic**
- ◇ **Usi previsti:** Retrofit elementi di fissaggio in calcestruzzo sottoposti a carico ciclico correlato a fatica, vedi allegato B /Annex B
- ◇ **Fabbricante:** MKT Metall-Kunststoff-Technik GmbH & Co.KG
Auf dem Immel 2
67685 Weilerbach
- ◇ **Sistemi di VVCP:** 1
- ◇ **Documento per la valutazione europea:** **EAD 330250-00-0601**
Valutazione tecnica europea: **ETA-17/0194, 14.03.2023**
Organismo di valutazione tecnica: DIBt, Berlin
Organismi notificati: NB 2873 – Technische Universität Darmstadt

◇ **Prestazioni dichiarate:**

| Caratteristiche essenziali | Prestazione |
|---|---------------------------------|
| Resistenza meccanica e stabilità (BWR 1) | |
| Resistenze caratteristiche sotto carico di trazione (effetti statici e quasi statici) | Allegato/Annex B2, B3, C4 |
| Resistenze caratteristiche sotto stress trasversale (effetti statici e quasi statici) | Allegato/Annex C5 |
| Turni (effetti statici e quasi statici) | Allegato/Annex C6 |
| Resistenza caratteristica e turni per la categoria di prestazioni sismiche C1+C2 | Allegato/Annex C4 – C6 |
| Resistenza alla fatica caratteristica sotto sforzo di trazione ciclico | Allegato/Annex C1 – C3 |
| Resistenza alla fatica caratteristica sotto carichi trasversali ciclici | |
| Resistenza alla fatica caratteristica in combinazione ciclica carichi di trazione e trasversali | |
| Carico fattore di trasferimento per ciclico carichi di trazione e trasversali | |
| Igiene, salute e ambiente (BWR 3) | |
| Contenuto, emissione e / o rilascio di sostanze pericolose | Nessuna prestazione determinata |


La prestazione del prodotto sopra identificato è conforme all'insieme delle prestazioni dichiarate. La presente dichiarazione di responsabilità viene emessa, in conformità al regolamento (UE) n. 305/2011, sotto la sola responsabilità del fabbricante sopra identificato.

Firmato a nome e per conto del fabbricante da:



Stefan Weustenhagen
(Direttore Generale)
Weilerbach, 14.03.2023

p.p.



Dipl.-Ing. Detlef Bigalke
(Direttore del Sviluppo del Prodotto)



L'originale di questa dichiarazione di prestazione è stata scritta in tedesco. In caso di deviazioni nella traduzione, la versione tedesca è valida.

Specifications of intended use

| Injection System VMZ dynamic | 100 M12 | 125 M16 | 170 M20 |
|--|------------------|---|---------|
| Fatigue cyclic loading | | ✓ | |
| Static and quasi-static action | | ✓ | |
| Seismic action (Category C1 + C2) | | ✓ | |
| Cracked or uncracked concrete | | ✓ | |
| Strength classes acc. to EN 206:2013+A1:2016 | | C20/25 to C50/60 | |
| Compacted reinforced or unreinforced normal weight concrete without fibers acc. to EN 206:2013+A1:2016 | | ✓ | |
| Temperature range I | -40 °C to +80 °C | maximum long-term temperature +50 °C maximum short-term temperature +80 °C | |

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions: all materials
- For all other conditions:
Intended use of materials according to Annex A4, Table A1 corresponding to the corrosion resistance class CRC to EN 1993-1-4:2015

Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.)
- Anchorages are designed according to:
 - EOTA TR 061:2020 (Design method I and II) or
 - EN 1992-4:2018

Installation:

- Anchor shall only be used as a complete fastening unit delivered in series. Components of the anchor must not be replaced.
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the site manager.
- Installation admissible in dry and wet concrete and in water-filled borehole.
- Drill hole must be cleaned directly prior to installation of the anchor or the drill hole has to be protected against re-contamination in an appropriate way until dispensing the mortar in the drill hole.
- Water filled drill holes must not be polluted – otherwise the cleaning of the drill hole must be repeated.
- The anchor component installation temperature shall be at least +5 °C; during curing of the injection mortar the temperature of the concrete must not fall below -15 °C (for the standard variation of temperature after installation).
- It must be ensured that icing does not occur in the drill hole.
- Installation direction D3: vertically downwards and upwards as well as horizontally.
- Drilling by hammer drill bit, compressed air drill or vacuum drill bit.
- The filling of the annular gap can be omitted if it is ensured that the anchor is only loaded in axial direction.

Injection System VMZ dynamic

Intended use
Specifications

Annex B1

Table B1: Installation parameters


| Anchor size / version | | | 100 M12 | 100 M12 A4 100 M12 HCR | 125 M16 | 125 M16 A4 125 M16 HCR | 170 M20 |
|---|--------------------|------|----------------|---------------------------|----------------|---------------------------|----------------|
| Effective anchorage depth | $h_{ef} \geq$ | [mm] | 100 | | 125 | | 170 |
| Nominal diameter of drill hole | $d_0 =$ | [mm] | 14 | | 18 | | 24 |
| Depth of drill hole ¹⁾ | $h_0 \geq$ | [mm] | 105 | | 130 | | 180 |
| Diameter of cleaning brush | $D \geq$ | [mm] | 15,0 | | 19,0 | | 25,0 |
| Installation torque | $T_{inst} =$ | [Nm] | 30 | | 50 | | 80 |
| Diameter of clearance hole in the fixture | $d_f =$ | [mm] | 15 | | 19 | | 25 |
| Fixture thickness ²⁾ | $t_{fix,min} \geq$ | [mm] | 12 | | 16 | | 20 |
| | $t_{fix,max} \leq$ | [mm] | 200 | | | | |
| Overstand | $h_p =$ | [mm] | $31 + t_{fix}$ | $24 + t_{fix}$ | $39 + t_{fix}$ | $30 + t_{fix}$ | $48 + t_{fix}$ |

¹⁾ If the present fixture thickness is lower than the maximum fixture thickness of the anchor, the depth of drill hole should be increased accordingly


²⁾ $t_{fix,min}$ may be replaced by $t_{fix,min,red}$, if, when determining the anchor under the highest load, the action ΔV_{Ed} is smaller than the fatigue resistance in transverse direction

$$t_{fix,min,red} = \left(0,5 + 0,5 \cdot \frac{\Delta V_{Ed}}{\Delta V_{Rd,s,E,n} * \psi_{FV}} \right) \cdot t_{fix,min}$$

Pre-setting installation



Through-setting installation



Injection System VMZ dynamic

Intended use
Installation parameters

Annex B2

Table B2: Minimum thickness of concrete and minimum spacing and edge distance

| Anchor size | | | 100 M12 | 125 M16 | 170 M20 |
|--------------------------------------|-----------|------|------------|------------|-------------|
| Minimum thickness of concrete member | h_{min} | [mm] | 130 | 160 | 220 |
| Cracked concrete | | | | | |
| Minimum spacing | s_{min} | [mm] | 50 | 60 | 80 |
| Minimum edge distance ¹⁾ | c_{min} | [mm] | 70 (50) | 80 (60) | 110 (80) |
| Uncracked concrete | | | | | |
| Minimum spacing | s_{min} | [mm] | 80 | 60 | 80 |
| Minimum edge distance | c_{min} | [mm] | 75 | 80 | 110 |

¹⁾ Values in brackets are valid if edge reinforcement $d = 8$ mm is installed

Injection System VMZ dynamic

Intended use
Minimum thickness of concrete, spacing and edge distances

Annex B3

Table B3: Processing time and curing time, VMZ

| Temperature in the drill hole | Maximum processing time | Minimum curing time in dry concrete ¹⁾ |
|--|-------------------------|---|
| - 15 °C to - 10 °C | 45 min | 7 d |
| - 9 °C to - 5 °C | 45 min | 10:30 h |
| - 4 °C to - 1 °C | 45 min | 6:00 h |
| 0 °C to + 4 °C | 20 min | 3:00 h |
| + 5 °C to + 9 °C | 12 min | 2:00 h |
| + 10 °C to + 19 °C | 6 min | 1:20 h |
| + 20 °C to + 29 °C | 4 min | 45 min |
| + 30 °C to + 34 °C | 2 min | 25 min |
| + 35 °C to + 39 °C | 1,4 min | 20 min |
| + 40 °C | 1,4 min | 15 min |
| Cartridge temperature $\geq 5^{\circ}\text{C}$ | | |

¹⁾ Curing time in wet concrete shall be doubled

Table B4: Processing time and curing time, VMZ express

| Temperature in the drill hole | Maximum processing time | Minimum curing time in dry concrete ¹⁾ |
|--|-------------------------|---|
| - 5 °C to - 1 °C | 20 min | 4:00 h |
| 0 °C to + 4 °C | 10 min | 2:00 h |
| + 5 °C to + 9 °C | 6 min | 1:00 h |
| + 10 °C to + 19 °C | 3 min | 40 min |
| + 20 °C to + 29 °C | 1 min | 20 min |
| + 30 °C | 1 min | 10 min |
| Cartridge temperature $\geq 5^{\circ}\text{C}$ | | |

¹⁾ Curing time in wet concrete shall be doubled

Injection System VMZ dynamic

Intended use
Processing time and curing time

Annex B4

Installation instructions – Through-setting installation

| Hole drilling | | |
|--|------------------|--|
| 1 | | Drill hole perpendicular to concrete surface with hammer drill, compressed air drill or vacuum drill bit. |
| Cleaning Drill hole must be cleaned directly prior to installation of the anchor | | |
| all sizes | | <u>Cleaning with compressed air</u> |
| 2a | | Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times . |
| 2b | | Check diameter of Cleaning Brush. If brush can be pushed into the drill hole without any resistance, it must be replaced. Chuck brush into drill machine. Turn on drill machine. Brush drill hole back and forth along the entire drill hole depth at least two times while rotated by drill machine. |
| 2c | | Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times . |
| 2 | M12 - M16 | <u>Manual cleaning</u> (alternative cleaning method) |
| 2a | | Blow out drill hole from the bottom using Blow-out Pump at least two times . |
| 2b | | Check diameter of Cleaning Brush. If brush can be pushed into the drill hole without any resistance, it must be replaced. Chuck brush into drill machine. Turn on drill machine. Brush drill hole back and forth along the entire drill hole depth at least two times while rotated by drill machine. |
| 2c | | Blow out drill hole from the bottom using Blow-out Pump at least two times . |








Injection System VMZ dynamic

Intended use

Installation instructions – Through-setting installation

Annex B5

Installation instructions – Through-setting installation (continuation)

| Injection | | |
|-------------------------|---|--|
| 3 |  | Check minimum shelf-life on VMZ cartridge. Never use when expired. Remove cap from VMZ cartridge. Screw static mixer on cartridge. When using a new cartridge always use a new static mixer. Never use cartridge without static mixer and never use static mixer without helix inside. |
| 4 |  | Insert cartridge in dispenser. Before injecting discard mortar (at least 2 full strokes or a line of 10 cm) until it shows a consistent grey colour. Never use this mortar. |
| 5 |  | Prior to injection, check if static mixer reaches the bottom of the drill hole. If it does not reach the bottom, plug mixer extension onto static mixer, in order to properly fill the drill hole. Fill hole with a sufficient quantity of injection mortar. Start from the bottom of the drill hole and work out to avoid trapping air pockets. |
| Insertion of anchor rod | | |
| 6 |  | Insert the pre-assembled anchor within processing time by hand, rotating slightly up to the full embedment depth, until the conical washer is in contact with the fixture. The anchor rod is properly set when the annular gap between anchor rod and fixture is completely filled. If no mortar is visible on the surface of the fixture, pull out the anchor rod immediately, let the mortar cure, drill out the hole and start again from step 2. |
| 7 |  | Follow minimum curing time shown in Annex B4 as well as on cartridge label. During curing time anchor rod must not be moved or loaded. |
| 8 |  | Remove excess mortar after curing time. Remove locknut. |
| 9 |  | 1. Apply installation torque T_{INST} according to Table B1 by using torque wrench. 2. Screw on locknut until hand tight then tighten $\frac{1}{4}$ to $\frac{1}{2}$ turn using a screw wrench. |

Injection System VMZ dynamic

Intended use
Installation instructions – Through-setting installation (continuation)

Annex B6

Installation instructions – Pre-setting installation









| Hole drilling | | |
|--|------------------|--|
| 1 | | Drill perpendicular to concrete surface with hammer drill, vacuum drill or compressed air drill. |
| Cleaning Drill hole must be cleaned directly prior to installation of the anchor | | |
| all sizes | | <u>Cleaning with compressed air</u> |
| 2a | | Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times . |
| 2b | | Check diameter of Cleaning Brush. If brush can be pushed into the drill hole without any resistance, it must be replaced. Chuck brush into drill machine. Turn on drill machine. Brush drill hole back and forth along the entire drill hole depth at least two times while rotated by drill machine. |
| 2c | | Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times . |
| 2 | M12 - M16 | <u>Manual cleaning</u> (alternative cleaning method) |
| 2a | | Blow out drill hole from the bottom using Blow-out Pump at least two times . |
| 2b | | Check diameter of Cleaning Brush. If brush can be pushed into the drill hole without any resistance, it must be replaced. Chuck brush into drill machine. Turn on drill machine. Brush drill hole back and forth along the entire drill hole depth at least two times while rotated by drill machine. |
| 2c | | Blow out drill hole from the bottom using Blow-out Pump at least two times . |

Injection System VMZ dynamic

Intended use
Installation instructions – Pre-setting installation

Annex B7

Installation instructions – Pre-setting installation (continuation)

| Injection | | |
|-------------------------|---|---|
| 3 |  | Check minimum shelf-life on VMZ cartridge. Never use when expired. Remove cap from VMZ cartridge. Screw static mixer on cartridge. When using a new cartridge always use a new Mixer Nozzle. Never use cartridge without static mixer and never use static mixer without helix inside. |
| 4 |  | Insert cartridge in Dispenser. Before injecting discard mortar (at least 2 full strokes or a line of 10 cm) until it shows a consistent grey colour. Never use this mortar. |
| 5 |  | Prior to injection check if static mixer reaches the bottom of the drill hole. If it does not reach the bottom, plug mixer extension onto static mixer in order to properly fill the drill hole. Fill hole with a sufficient quantity of injection mortar. Start from the bottom of the drill hole and work out to avoid trapping air pockets. |
| Insertion of anchor rod | | |
| 6 |  | Mark the embedment depth on the anchor rod. Insert the anchor rod by hand, rotating slightly up within processing time. The anchor rod is properly set when excess mortar seeps from the hole. If the hole is not completely filled, pull out anchor rod, let mortar cure, drill out hole and start again from step 2. |
| 7 |  | Follow minimum curing time shown in Annex B4 as well as on cartridge label. During curing time anchor rod must not be moved or loaded. |
| 8 |  | Remove excess mortar after curing time. |
| 9 |  | <ol style="list-style-type: none"> 1. Fixture, washer and nut (without centring ring) can be mounted. 2. Apply installation torque T_{inst} according to Table B1 by using torque wrench. 3. Screw on locknut hand-tight then tighten $\frac{1}{4}$ to $\frac{1}{2}$ turn using a screw wrench. |
| 10 |  | Annular gap between anchor rod and fixture must be filled with injection mortar through the bore of the conical washer using the adapter plugged onto the static mixer. The annular gap is properly filled when excess mortar seeps out. |

Injection System VMZ dynamic






Intended use
Installation instructions – Pre-setting installation (continuation)

Annex B8

Installation instructions – Installation with clearance between concrete and anchor plate (if the fastener is only loaded in axial direction)

Work steps 1 - 5 as illustrated in Annex B5 and B6

Insertion of anchor rod

| | | |
|-----------|---|--|
| 6 |  | Inserting the pre-assembled anchor within processing time by hand, rotating slightly until the conical washer lies against the fixture. |
| 7 |  | Check for excess mortar seeping out of the hole. If the hole is not completely filled, pull out anchor rod, let mortar cure, drill out hole and start again from step 2. The annular gap in the fixture does not have to be filled. |
| 8 |  | Follow minimum curing time shown in Annex B4 as well as on cartridge label. During curing time anchor rod must not be moved or loaded. |
| 9 |  | Remove locknut after curing time and backfilling of anchor plate. |
| 10 |  | 1. Apply installation torque T_{inst} according to Annex B2 (Table B1) by using torque wrench. 2. Screw on locknut hand-tight then tighten $\frac{1}{4}$ to $\frac{1}{2}$ turn using a screw wrench. |

Injection System VMZ dynamic

Intended use

Installation instructions – Installation with clearance between concrete and anchor plate

Annex B9

Table C1: Characteristic values of the fatigue resistance under tension load after n load cycles without static actions ($F_{Elod} = 0$) design method I according to TR 061

| Anchor size / version | | | 100 M12 | 100 M12 A4 100 M12 HCR | 125 M16 | 125 M16 A4 125 M16 HCR | 170 M20 |
|--|-----------------------------|---|---------|---------------------------|---------|---------------------------|---------|
| Steel failure | | | | | | | |
| Characteristic resistance without static actions | [kN] | $\Delta N_{Rk,s,0,n}$ | | | | | |
| Number of load cycles n | 1 | 53,9 | 53,9 | 83,4 | 83,4 | 112,1 | |
| | $\leq 10^3$ | 48,3 | 52,6 | 78,8 | 72,5 | 92,7 | |
| | $\leq 3 \cdot 10^3$ | 45,9 | 50,9 | 77,1 | 68,2 | 89,9 | |
| | $\leq 10^4$ | 41,4 | 47,6 | 73,1 | 62,4 | 83,4 | |
| | $\leq 3 \cdot 10^4$ | 35,9 | 42,8 | 66,3 | 56,7 | 73,8 | |
| | $\leq 10^5$ | 29,1 | 36,3 | 55,8 | 50,5 | 60,9 | |
| | $\leq 3 \cdot 10^5$ | 24,2 | 30,1 | 45,5 | 45,7 | 50,7 | |
| | $\leq 10^6$ | 21,1 | 24,9 | 37,4 | 41,8 | 44,9 | |
| | $> 10^6$ | 20,1 | 21,2 | 34,0 | 37,3 | 43,5 | |
| Partial factor | $\gamma_{Ms,fat,n}$ [-] | according to TR 061, Eq. (3) | | | | | |
| Exponent for combined loading | α_{sn} [-] | 1,5 | 1,2 | 1,5 | 1,5 | 1,5 | |
| Pull-out | | | | | | | |
| Characteristic resistance without static actions | $\Delta N_{Rk,p,0,n}$ [kN] | $(\Delta N_{Rk,s,0,n} / \gamma_{Ms,fat,n}) \cdot \gamma_{Mp,fat}$ | | | | | |
| Partial factor | $\gamma_{Mp,fat}$ [-] | 1,5 | | | | | |
| Concrete failure | | | | | | | |
| Characteristic resistance without static actions | $\Delta N_{Rk,c,0,n}$ [kN] | $\eta_{k,c,N,fat,n} \cdot N_{Rk,c}^{1)}$ | | | | | |
| | $\Delta N_{Rk,sp,0,n}$ [kN] | $\eta_{k,c,N,fat,n} \cdot N_{Rk,sp}^{1)}$ | | | | | |
| Reduction factor | [-] | $\eta_{k,c,N,fat,n}$ | | | | | |
| Number of load cycles n | 1 | 1,0 | | | | | |
| | $\leq 10^3$ | 0,932 | | | | | |
| | $\leq 3 \cdot 10^3$ | 0,893 | | | | | |
| | $\leq 10^4$ | 0,841 | | | | | |
| | $\leq 3 \cdot 10^4$ | 0,794 | | | | | |
| | $\leq 10^5$ | 0,750 | | | | | |
| | $\leq 3 \cdot 10^5$ | 0,722 | | | | | |
| | $\leq 10^6$ | 0,704 | | | | | |
| | $> 10^6$ | 0,693 | | | | | |
| Effective anchorage depth | h_{ef} [mm] | 100 | | 125 | | 170 | |
| Partial factor | $\gamma_{Mc,fat}$ [-] | 1,5 | | | | | |
| Exponent for combined loading | α_c [-] | 1,5 | | | | | |
| Load-transfer factor for fastener groups | ψ_{FN} [-] | 0,79 | | | | | |

¹⁾ see table C4

Injection System VMZ dynamic

Performance

Characteristic fatigue resistance under **tension load**, **design method I** according to TR 061

Annex C1

Table C2: Characteristic values of the fatigue resistance under shear load after n load cycles without static actions ($F_{E\text{lod}} = 0$) design method I according to TR 061

| Anchor size / version | | 100 M12 | 100 M12 A4 100 M12 HCR | 125 M16 | 125 M16 A4 125 M16 HCR | 170 M20 |
|--|-----------------------------|---|---------------------------|---------|---------------------------|---------|
| Steel failure | | | | | | |
| Characteristic resistance without static actions | [kN] | $\Delta V_{Rk,s,0,n}$ | | | | |
| Number of load cycles n | 1 | 34,0 | | 63,0 | 149,0 | |
| | $\leq 10^3$ | 27,6 | 31,3 | 54,0 | 113,5 | |
| | $\leq 3 \cdot 10^3$ | 23,8 | 28,3 | 47,2 | 91,6 | |
| | $\leq 10^4$ | 18,6 | 23,5 | 36,5 | 65,0 | |
| | $\leq 3 \cdot 10^4$ | 14,1 | 18,1 | 26,2 | 43,9 | |
| | $\leq 10^5$ | 10,5 | 12,8 | 18,4 | 29,0 | |
| | $\leq 3 \cdot 10^5$ | 8,9 | 9,8 | 15,6 | 23,2 | |
| | $\leq 10^6$ | 8,2 | 8,5 | 15,0 | 21,3 | |
| | $> 10^6$ | 8,2 | | 15,0 | 21,1 | |
| Partial factor | $\gamma_{Ms,fat,n}$ [-] | according TR 061, Eq. (3) | | | | |
| Exponent for combined loading | α_{sn} [-] | 1,5 | 1,2 | 1,5 | 1,5 | 1,5 |
| Concrete failure | | | | | | |
| Characteristic resistance without static actions | $\Delta V_{Rk,cp,0,n}$ [kN] | $\eta_{k,c,V,fat,n} \cdot V_{Rk,cp}^{1)}$ | | | | |
| | $\Delta V_{Rk,c,0,n}$ [kN] | $\eta_{k,c,V,fat,n} \cdot V_{Rk,c}^{1)}$ | | | | |
| Reduction factor | [-] | $\eta_{k,c,N,fat,n}$ | | | | |
| Number of load cycles n | 1 | 1,0 | | | | |
| | $\leq 10^3$ | 0,799 | | | | |
| | $\leq 3 \cdot 10^3$ | 0,760 | | | | |
| | $\leq 10^4$ | 0,725 | | | | |
| | $\leq 3 \cdot 10^4$ | 0,700 | | | | |
| | $\leq 10^5$ | 0,680 | | | | |
| | $\leq 3 \cdot 10^5$ | 0,668 | | | | |
| | $\leq 10^6$ | 0,660 | | | | |
| | $> 10^6$ | 0,652 | | | | |
| Effective anchor length | l_f [mm] | 100 | | 125 | | 170 |
| Outside diameter | d_{nom} [mm] | 14 | | 18 | | 24 |
| Partial factor | $\gamma_{Mc,fat}$ [-] | 1,5 | | | | |
| Exponent for combined loading | α_c [-] | 1,5 | | | | |
| Load-transfer factor for fastener groups | ψ_{FV} [-] | 0,81 | | | | |

¹⁾ see table C4

Injection System VMZ dynamic

Performance

Characteristic fatigue resistance under **shear load** for **design method I** according to **TR 061**

Annex C2

Table C3: Characteristic fatigue limit resistance for design according to EN 1992-4:2018 and design method II according to TR 061

| Anchor size / version | | | 100 M12 | 100 M12 A4 100 M12 HCR | 125 M16 | 125 M16 A4 125 M16 HCR | 170 M20 |
|--|-----------------------------|------|--|---------------------------|---------|---------------------------|-----------------|
| Tension load | | | | | | | |
| Steel failure | | | | | | | |
| Characteristic fatigue resistance | $\Delta N_{Rk,s,0,\infty}$ | [kN] | 20,1 | 21,2 | 34,0 | 37,3 | 43,5 |
| Partial factor | $\gamma_{Ms,fat}$ | [-] | 1,35 | | | | |
| Load-transfer factor for fastener groups | ψ_{FN} | [-] | 0,79 | | | | |
| Pull-out | | | | | | | |
| Characteristic fatigue resistance | $\Delta N_{Rk,p,0,\infty}$ | [kN] | $(\Delta N_{Rk,s,0,\infty} / \gamma_{Ms,N,fat}) \cdot \gamma_{Mp,fat}$ | | | | |
| Partial factor | $\gamma_{Mp,fat}$ | [-] | 1,5 | | | | |
| Concrete failure | | | | | | | |
| Characteristic fatigue resistance | $\Delta N_{Rk,c,0,\infty}$ | [kN] | 0,693 $N_{Rk,c}$ ¹⁾ | | | | |
| | $\Delta N_{Rk,sp,0,\infty}$ | [kN] | 0,693 $N_{Rk,sp}$ ¹⁾ | | | | |
| Effective anchorage depth | h_{ef} | [mm] | 100 | | 125 | | 170 |
| Partial factor | $\gamma_{Mc,fat}$ | [-] | 1,5 | | | | |
| Shear load | | | | | | | |
| Steel failure without lever arm | | | | | | | |
| Characteristic fatigue resistance | $\Delta V_{Rk,s,0,\infty}$ | [kN] | 8,2 | | 15,0 | | 21,1 |
| Partial factor | $\gamma_{Ms,fat}$ | [-] | 1,35 | | | | |
| Load-transfer factor for fastener groups | ψ_{FV} | [-] | 0,81 | | | | |
| Concrete pry-out failure | | | | | | | |
| Characteristic fatigue resistance | $\Delta V_{Rk,cp,0,\infty}$ | [kN] | 0,652 $V_{Rk,cp}$ ¹⁾ | | | | |
| Partial factor | $\gamma_{Mc,fat}$ | [-] | 1,5 | | | | |
| Concrete edge failure | | | | | | | |
| Characteristic fatigue resistance | $\Delta V_{Rk,c,0,\infty}$ | [kN] | 0,652 $V_{Rk,c}$ ¹⁾ | | | | |
| Effective length of anchor | l_r | [mm] | 100 | | 125 | | 170 |
| Outside diameter of anchor | d_{nom} | [mm] | 14 | | 18 | | 24 |
| Partial factor | $\gamma_{Mc,fat}$ | [-] | 1,5 | | | | |
| Exponents for combined loading | α_s | [-] | 1,5 | 1,2 | 1,5 | | 1,5 |
| | α_{sn} | [-] | | | | | |
| | α_c | [-] | 1,5 | | | | |
| Injection System VMZ dynamic | | | | | | | Annex C3 |
| Performance Characteristic fatigue limit resistance for design according to EN 1992-4 and design method II according to TR 061 | | | | | | | |

Table C4: Characteristic values under tension load for static and quasi-static or seismic action

| Anchor size / version | | | 100 M12 100 M12 A4 100 M12 HCR | 125 M16 125 M16 A4 125 M16 HCR | 170 M20 | |
|---|---------------------------------------|------------------|--------------------------------------|--|------------------|--------------------|
| Steel failure | | | | | | |
| Characteristic resistance | $N_{RK,s}$ | [kN] | 57 | 111 | 188 | |
| | $N_{RK,s,C1}$ $N_{RK,s,C2}$ | | | | | |
| Partial factor | γ_{Ms} | [-] | 1,5 | | | |
| Pull-out failure | | | | | | |
| Characteristic resistance (C20/25) | uncracked concrete | $N_{RK,p}$ | [kN] | 49,2 | 68,8 | 109 |
| | cracked concrete | $N_{RK,p}$ | [kN] | 34,4 | 48,1 | 76,3 |
| | seismic C1 | $N_{RK,p,C1}$ | [kN] | 36,0 | 43,7 | 88,2 |
| | seismic C2 | $N_{RK,p,C2}$ | [kN] | 17,6 | 26,1 | 59,7 |
| Concrete cone failure | | | | | | |
| Characteristic edge distance | $c_{cr,N}$ | [mm] | $1,5 \cdot h_{ef}$ | | | |
| Factor k1 | uncracked concrete | $k_{ucr,N}$ | [-] | 11,0 | | |
| | cracked concrete | $k_{cr,N}$ | [-] | 7,7 | | |
| Effective anchorage depth | h_{ef} | [mm] | 100 | 125 | 170 | |
| Splitting | | | | | | |
| For each proof of splitting failure, $N_{RK,sp}$ shall be calculated according to EN 1992-4:2018, equation (7.23). The higher value for $N_{RK,sp}$ of case 1 and case 2 may be applied for the design. | | | | | | |
| Standard thickness of concrete | | $h_{min,1} \geq$ | [mm] | 200 | 250 | 340 |
| Case 1 | Characteristic resistance (C20/25) | $N^0_{RK,sp}$ | [kN] | 40 | 50 | 109 |
| | Characteristic edge distance | $c_{cr,sp}$ | [mm] | $1,5 \cdot h_{ef}$ | | |
| Case 2 | Characteristic resistance | $N^0_{RK,sp}$ | [kN] | min [$N_{RK,p}$; $N^0_{RK,c}$] | | |
| | Characteristic edge distance | $c_{cr,sp}$ | [mm] | $2 \cdot h_{ef}$ | $2 \cdot h_{ef}$ | $1,5 \cdot h_{ef}$ |
| Minimum thickness of concrete | | $h_{min,2} \geq$ | [mm] | 130 | 160 | 220 |
| Case 1 | Characteristic resistance (C20/25) | $N^0_{RK,sp}$ | [kN] | 30 | 40 | 75 |
| | Characteristic edge distance | $c_{cr,sp}$ | [mm] | $1,5 \cdot h_{ef}$ | | |
| Case 2 | Characteristic resistance | $N^0_{RK,sp}$ | [kN] | min [$N_{RK,p}$; $N^0_{RK,c}$] | | |
| | Characteristic edge distance | $c_{cr,sp}$ | [mm] | $3 \cdot h_{ef}$ | $3 \cdot h_{ef}$ | $2,6 \cdot h_{ef}$ |
| Increasing factor for $N_{RK,p}$ and $N^0_{RK,sp}$ (case 1) | | ψ_c | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,5}$ | | |
| Installation factor | | γ_{inst} | [-] | 1,0 | | |

Injection System VMZ dynamic

Performance

Characteristic values for **tension load** under **static and quasi static** or **seismic action**

Annex C4

Table C5: Characteristic values under shear load for static and quasi-static or seismic action

| Anchor size / version | | | 100 M12 100 M12 A4 100 M12 HCR | 125 M16 125 M16 A4 125 M16 HCR | 170 M20 |
|---|-----------------|------|--------------------------------------|--------------------------------------|---------|
| Steel failure without lever arm | | | | | |
| Characteristic resistance | $V_{Rk,s}^0$ | [kN] | 34 | 63 | 149 |
| | $V_{Rk,s,C1}^0$ | [kN] | 27,2 | 39,1 | 82,3 |
| | $V_{Rk,s,C2}^0$ | [kN] | 27,2 | 50,4 | 108,8 |
| Partial factor | γ_{Ms} | [-] | 1,25 | | |
| Ductility factor | k_7 | [-] | 1,0 | | |
| Steel failure with lever arm | | | | | |
| Characteristic bending resistance | $M_{Rk,s}^0$ | [Nm] | 105 | 266 | 519 |
| Partial factor | γ_{Ms} | [-] | 1,25 | | |
| Concrete pry-out failure | | | | | |
| Pry-out factor | k_8 | [-] | 2,0 | | |
| Concrete edge failure | | | | | |
| Effective length of anchor in shear load | l_f | [mm] | 100 | 125 | 170 |
| Diameter of anchor | d_{nom} | [mm] | 14 | 18 | 24 |
| Installation factor | γ_{inst} | [-] | 1,0 | | |
| Factor for anchorages with filled annular gap | α_{gap} | [-] | 1,0 | | |

Injection System VMZ dynamic

Performance
Characteristic values under **shear load** for **static and quasi-static** or **seismic action**

Annex C5

Table C6: Displacements under tension load for static and quasi-static or seismic action

| Anchor size / version | | | 100 M12 100 M12 A4 100 M12 HCR | 125 M16 125 M16 A4 125 M16 HCR | 170 M20 |
|---|----------------------|------|--------------------------------------|--------------------------------------|---------|
| Tension load in cracked concrete | N | [kN] | 17,1 | 24 | 38 |
| Displacements | δ_{N0} | [mm] | 0,6 | 0,7 | 0,8 |
| | $\delta_{N\infty}$ | [mm] | 1,3 | 1,3 | 1,3 |
| Tension load in uncracked concrete | N | [kN] | 24 | 33 | 53,3 |
| Displacements | δ_{N0} | [mm] | 0,4 | 0,6 | 0,6 |
| | $\delta_{N\infty}$ | [mm] | 1,3 | 1,3 | 1,3 |
| Displacements under seismic tension loads C2 | | | | | |
| Displacements | $\delta_{N,C2(DLS)}$ | [mm] | 1,1 | 1,5 | 1,9 |
| | $\delta_{N,C2(ULS)}$ | [mm] | 3,0 | 4,4 | 4,5 |

Table C7: Displacements under shear load for static and quasi-static or seismic action

| Anchor size / version | | | 100 M12 100 M12 A4 100 M12 HCR | 125 M16 125 M16 A4 125 M16 HCR | 170 M20 |
|---|----------------------|------|--------------------------------------|--------------------------------------|---------|
| Shear load | V | [kN] | 19,3 | 36 | 75 |
| Displacements | δ_{V0} | [mm] | 3,3 | 3,8 | 4,3 |
| | $\delta_{V\infty}$ | [mm] | 5,0 | 5,7 | 6,5 |
| Displacements under seismic shear loads C2 | | | | | |
| Displacements | $\delta_{V,C2(DLS)}$ | [mm] | 2,5 | 2,9 | 3,5 |
| | $\delta_{V,C2(ULS)}$ | [mm] | 5,1 | 6,8 | 9,3 |

Injection System VMZ dynamic

Performance
Displacements under **static and quasi-static** or **seismic action**

Annex C6